



Product	Type
----------------	-------------

EZ-MULZ™ 5610

Metal Processing

Emulsifier Base for Paraffinic Oil

Application

EZ-Mulz 5610 is an emulsifier base designed to emulsify paraffinic oils with aniline points of 180°F to 220°F.

Based on natural sodium sulfonate, secondary emulsifiers and other components, EZ-Mulz 5610 is ideal for formulating soluble oils.

EZ-Mulz 5610 is free from chlorine, nitrites, phenols and heavy metals.

Typical Properties

Test	Typical
Appearance	Dark brown, viscous fluid
Specific gravity at 25° C	1.04
Water wt. %	9.0
Total acid value, mg KOH/g	24
pH at 1.0% in water	8.4

Benefits

- Excellent emulsion stability in all paraffinic oils
- Good corrosion protection in for ferrous metals
- Adds lubricity
- Compatible with extreme pressure additives such as chlorinated or sulfurized compounds

Performance

Corrosion on cast iron ships – ASTM D-4627-92
Ratings scale: 0 = no rust and 5 = 100% rust

5% emulsion of 15% EZ-Mulz 5610 in oil.....0

Typical Applications

EZ-Mulz 5610 can be used in several metalworking applications. For example:

Use the following as a guideline, balance formula as needed

General-purpose soluble oil

% by weight

100 SUS paraffinic oil.....	65 - 85
EZ-Mulz 5610	15 - 25
Chlorinated additive (Extreme pressure agent).....	0 - 20
Glycol ether (To modify viscosity)	0 - 1
Biocide.....	0 - 3
Fungicide.....	0 - 1
Defoamer, if necessary	0 - 1

Adding some biocides may require the addition of tall oil fatty acid to balance the formula.

Storage and Handling

Recommended Maximum Long Term Storage Temperature*	Ambient
Recommended Minimum Temperature for Use	Ambient
Flash Point	>150°C COC

*Do not store with excessive heat (>150° F) over long periods.



Lockhart Chemical Company

4302 James P Cole Boulevard Flint, MI 48505
Phone: 1-810-789-8330 Fax:1-810-789-3266

www.lockhartchem.com

email: customerservice@lockhartchem.com

DISCLAIMER: To the best of our knowledge, the information and recommendations contained herein are accurate. However, this information and recommendations are furnished without any warranty, representation or license of any kind. Users of our products are encouraged to run their own tests to ensure product fitness for their applications. Furthermore, users assume sole liability for any patent infringement that occurs by reason of following our recommendations or using the information given

EZ-Mulz is a Trademark of the Lockhart Chemical Company

2/1/2017

