



<b>Product</b>	<b>Type</b>
----------------	-------------

**EZ-MULZ™ 5900**

**Metal Processing**

**Emulsifier Base for Paraffinic Oil**

**Application**

EZ-Mulz 5900 is an emulsifier base designed to emulsify paraffinic oils with high aniline points.

Based on natural sodium sulfonate, secondary emulsifiers and other components, EZ-Mulz 5900 is ideal for formulating soluble oils.

EZ-Mulz 5900 is free from chlorine, nitrites, phenols and heavy metals.

**Typical Properties**

Test	Typical
Appearance	Dark brown, viscous fluid
Specific gravity at 25° C	1.01
Water wt. %	6.0
Total acid value, mg KOH/g	25
pH at 1.0% in water	8.5

**Benefits**

- Excellent emulsion stability in all paraffinic oils
- Good corrosion protection in for ferrous metals
- Adds lubricity
- Compatible with extreme pressure additives such as chlorinated or sulfurized compounds

**Performance**

Corrosion on cast iron ships – ASTM D-4627-92  
Ratings scale: 0 = no rust and 5 = 100% rust

**5% emulsion of 15% EZ-Mulz 5900 in oil.....0**

## Typical Applications

**EZ-Mulz 5900** can be used in several metalworking applications. For example:

*Use the following as a guideline, balance formula as needed*

### General-purpose soluble oil

	<u>% by weight</u>
150 SUS paraffinic oil.....	65 - 85
<b>EZ-Mulz 5900</b> .....	15 – 25
Chlorinated additive (Extreme pressure agent).....	0 - 20
Biocide.....	0 – 3
Fungicide.....	0 – 1
Defoamer, if necessary .....	0 – 1

*Adding some biocides may require the addition of tall oil fatty acid to balance the formula.*

## Storage and Handling

Recommended Maximum Long Term Storage Temperature*	Ambient
Flash Point	>150°C COC

\*Do not store with excessive heat (>150° F) over long periods.



### **Lockhart Chemical Company**

4302 James P Cole Boulevard Flint, MI 48505  
Phone: 1-810-789-8330 Fax:1-810-789-3266  
[www.lockhartchem.com](http://www.lockhartchem.com)  
email: [customerservice@lockhartchem.com](mailto:customerservice@lockhartchem.com)

**DISCLAIMER:** To the best of our knowledge, the information and recommendations contained herein are accurate. However, this information and recommendations are furnished without any warranty, representation or license of any kind. Users of our products are encouraged to run their own tests to ensure product fitness for their applications. Furthermore, users assume sole liability for any patent infringement that occurs by reason of following our recommendations or using the information given