

Product	Type
---------	------

COUNTER RUST™ 855
Rust Preventive

Premium thin-film barium sulfonate based water displacing rust preventive soluble in oil and solvent

Application

Counter Rust 855 is a cost effective, thin-film, water displacing rust preventive based on barium sulfonate. Counter Rust 855 provides excellent protection against salt and humid atmospheres when formulated in petroleum solvent and/or oil solutions.

Counter Rust 855 is designed specifically to offer the quick demulsification time while providing excellent solubility and stability in the widest ranges of solvents, oils and blends. When formulated and tested in the B-117 salt atmosphere test, Counter Rust 855 has demonstrated over 75 hours of protection yet the film is easily removed. Even a 5% it offers over 60 days protection from humidity

Counter Rust 855 is non-staining on a variety of ferrous and non-ferrous metals.

Typical Properties

Test	Typical
Appearance	waxy solid
Specific gravity at 15.6° C	0.94
Total base number, mg KOH/g	16
Total saponification number, mg KOH/g	50
Congeal melt point, °C	36

Benefits

- Excellent salt spray and humidity protection for indoor and outdoor
- Non-Staining
- Good water-displacing and water-separation
- Soluble and stable in a wide variety of petroleum solvents and oils
- Light color and low odor
- Films are easily removed with Alkaline Cleaners

Suggested Formulations

Moisture displacing rust preventive coating:

Counter Rust 855	10.0 -20.0%
Mineral Spirits	Balance

Oily thin film finished rust preventive

Counter Rust 855	10.0 - 15.0%
100 SUS Paraffinic Oil	10.0 – 20.0%
Aliphatic High Flash Solvent	Balance

Storage and Handling

Recommended Maximum Long Term Storage Temperature*	Ambient
Recommended Minimum Temperature for Use	45°C / 113°F
Flash Point	150° C COC

*Long term storage at temperatures above this may result in loss of performance.



Lockhart Chemical Company
4302 James P Cole Boulevard Flint, MI 48505
Phone: 1-810-789-8330 Fax: 1-810-789-3266
www.lockhartchem.com
email: customerservice@lockhartchem.com

DISCLAIMER: To the best of our knowledge, the information and recommendations contained herein are accurate. However, this information and recommendations are furnished without any warranty, representation or license of any kind. Users of our products are encouraged to run their own tests to ensure product fitness for their applications. Furthermore, users assume sole liability for any patent infringement that occurs by reason of following our recommendations or using the information given.

Counter Rust is a Trademark of The Lockhart Chemical Company

11/8/2017